

Certificate of Analysis

Reference Material OxH199

Recommended Gold Concentration: 1.323 µg/g 95% Confidence Interval: +/- 0.011 μg/g

The above values apply only to product in jars or sachets which have an identification number within the following range: 577932–579615

Prepared and Certified By: Eoin Foster

Rocklabs Reference Materials

Scott Technology P.O. Box 18-142

Glen Innes Auckland 1743 **NEW ZEALAND**

Email: e.foster@scottautomation.com

Telephone: +64 9 6347696

Date of Certification: 07 August 2023

Certificate Status: Original

Available Packaging: This reference material has been packed in wide-

mouthed jars that contain 2.5 kg of product. The

contents of some jars may be subsequently repacked into sealed polyethylene sachets.

Origin of Reference Material: Basalt and feldspar minerals with minor

> quantities of finely divided gold-containing minerals that have been screened to ensure there

is no gold nugget effect.

Supplier of Reference Material: ROCKLABS

P O Box 18-142

Glen Innes

Auckland 1743 **NEW ZEALAND**

Email: rocklabs.sales@scottautomation.com

Website: www.rocklabs.com

Description:

The reference material is a light grey powder that has been well mixed. A homogeneity test was carried out after the entire batch was packaged into wide-mouthed jars. There is no soil component. The product contains crystalline quartz, so dust from it should not be inhaled.

| The app | proximate | chemical | composition | is: | | | |
|----------------------|-----------|----------|-------------|-----|--|--|--|
| (Uncertified Values) | | | | | | | |

| | (Uncertified values) | | |
|-----------|----------------------|-------|--|
| | | % | |
| SiO_2 | | 60.11 | |
| Al_2O_3 | | 15.97 | |
| Na_2O | | 3.45 | |
| K_2O | | 6.59 | |
| CaO | | 3.50 | |
| MgO | | 3.31 | |
| TiO_2 | | 1.03 | |
| MnO | | 0.08 | |
| P_2O_5 | | 0.27 | |
| Fe_2O_3 | | 5.16 | |
| LOI | | 0.73 | |

Intended Use:

This reference material is designed to be included with every batch of samples analysed and the results plotted for quality monitoring and assessment purposes.

Stability:

The container (jar or sachet) should not be heated to, or stored at temperatures higher than 50 °C. Where the container remains unopened, the reference material will remain stable for more than 10 years from the date of certification. When exposed to the atmosphere the reference material is stable, with total weight changes of less than 0.5 % at naturally occurring temperature and humidity extremes.

Method of Preparation:

This reference material has been produced under quality management systems certified to ISO 9001:2015

Following ILAC Guidelines G12:2000 and G13:2000, pulverized feldspar minerals and basalt rock were blended with finely pulverized and screened gold-containing minerals. Once the powders were uniformly mixed, the composite was placed into 1684 wide-mouthed jars, each bearing a unique number. 48 jars were randomly selected from the packaging run and material from these jars was used for both homogeneity and consensus testing.

Homogeneity Assessment:

Sampling was performed by Rocklabs, and an independent laboratory carried out gold analysis by fire assay of 30 g portions, using an ICP-AES finish. Steps were taken to minimize laboratory method variation in order to better detect any variation in the candidate reference material.

<u>Homogeneity</u>: A sample was removed from the top of each of the 48 jars randomly selected from the 1684 jars in the batch. The results of analysis of the 48 samples (randomly ordered then consecutively numbered before being sent to the laboratory) indicated produced a relative standard deviation of 1.5%

<u>Settling:</u> The contents of 6 randomly selected jars were compacted by vibration (to simulate the effect of freighting) and 5 samples were removed successively from top to bottom from each jar. In addition, 5 samples were removed from the last jar in the series. No top to bottom gradation in the gold values was observed.

Analytical Methodology:

Once homogeneity had been established, two sub-samples were submitted to a number of well-recognized laboratories in order to assign a gold value by consensus testing. The sub-samples were drawn from 48 randomly selected jars and each laboratory received samples from two different jars.

Each laboratory was instructed to analyse the samples for gold using the method they believed would give the best results. Indicative concentration ranges were given.

The samples were analysed for gold by all participating laboratories using fire assay followed by either gravimetric or instrument finish (AAS or ICP). The amount of sample used in the analyses varied between laboratories, (range 10 - 50g).

Calculation of Certified Value:

The 44 participating laboratories each returned replicate gold results using one finish method for both samples. Statistical analysis to identify outliers was carried out using the principles detailed in sections 7.3.2 - 7.3.4, ISO 5725-2: 1994. Assessment of each laboratory's performance was carried out on the basis of z-scores, partly based on the concept described in ISO/IEC Guide 43-1. Details of the criteria used in these examinations are available on request. As a result of these statistical analyses, 5 sets of results were excluded for the purpose of assigning a gold concentration value to this reference material. A recommended value was thus calculated from the average of the remaining n = 39 sets of replicate results. The 95% confidence interval was estimated using the formula:

$$X \pm ts/\sqrt{n}$$

(where X is the estimated average, s is the estimated standard deviation of the laboratory averages, and t is the 0.025 tail-value from Student's t-distribution with n-1 degrees of freedom). The recommended value is provided at the beginning of the certificate in $\mu g/g$ (ppm) units. A summary of the results used to calculate the recommended value is listed on page 4 and the names of the laboratories that

submitted results are listed on page 5. The results are listed in increasing order of the individual laboratory averages.

Statistical analysis of the consensus test results has been carried out by independent statistician, Dr Daniel Walsh.

Summary of Results Used to Calculate Gold Value

(Listed in increasing order of individual laboratory averages)

| | Gold ppm | * |
|-------------------------------------|----------|---------------|
| Sample 1 | Sample 2 | Set average |
| 1.252 | 1.251 | 1.252 |
| 1.260 | 1.260 | 1.260 |
| 1.291 | 1.258 | 1.274 |
| 1.280 | 1.270 | 1.275 |
| 1.284 | 1.286 | 1.285 |
| 1.290 | 1.295 | 1.292 |
| 1.252 | 1.338 | 1.295 |
| 1.291 | 1.303 | 1.297 |
| 1.290 | 1.310 | 1.300 |
| 1.300 | 1.310 | 1.305 |
| 1.290 | 1.320 | 1.305 |
| 1.330 | 1.290 | 1.310 |
| 1.300 | 1.320 | 1.310 |
| 1.310 | 1.310 | 1.310 |
| 1.320 | 1.310 | 1.315 |
| 1.320 | 1.320 | 1.320 |
| 1.320 | 1.320 | 1.320 |
| 1.330 | 1.310 | 1.320 |
| 1.350 | 1.290 | 1.320 |
| 1.350 | 1.290 | 1.320 |
| 1.315 | 1.330 | 1.322 |
| 1.340 | 1.310 | 1.325 |
| 1.345 | 1.315 | 1.330 |
| 1.335 | 1.325 | 1.330 |
| 1.340 | 1.320 | 1.330 |
| 1.325 | 1.340 | 1.332 |
| 1.325 | 1.340 | 1.332 |
| 1.322 | 1.344 | 1.333 |
| 1.370 | 1.300 | 1.335 |
| 1.345 | 1.330 | 1.337 |
| 1.350 | 1.333 | 1.341 |
| 1.360 | 1.330 | 1.345 |
| 1.330 | 1.370 | 1.350 |
| 1.350 | 1.365 | 1.357 |
| 1.370 | 1.360 | 1.365 |
| 1.390 | 1.350 | 1.370 |
| 1.380 | 1.370 | 1.375 |
| 1.380 | 1.380 | 1.380 |
| 1.420 | 1.420 | 1.420 |
| Average of the 39 sets | | 1.323 ppm |
| Standard deviation of the 39 sets | | 0.033 ppm |
| Relative standard deviation | | 2.5% |
| 95% confidence interval for average | | +/- 0.011 ppm |

Note: Neither the Standard deviation nor the Confidence interval should be used as a basis to set control limits when plotting individual laboratory results.

See notes under "Instructions and Recommendations for Use" (pg 6)

Participating Laboratories

Australia ALS Minerals, Kalgoorlie

ALS Minerals, Perth

ALS Minerals, Townsville

Bureau Veritas Amdel, Adelaide

Intertek Genalysis Laboratory Services, Perth

Burkina Faso ALS Minerals, Burkina Faso

Canada Actlabs Val dÓr

ALS Minerals, Vancouver ALS Minerals, Val d'Or

Bourlamaque Assay Laboratories, Quebec

Bureau Veritas Commodities Canada Ltd, Vancouver

MSALABS Inc., Langley BC

SGS Minerals Services, Lakefield, Ontario SGS Minerals Services, Vancouver

Techni-lab, Ste-Germaine-Boule

Chile ALS Minerals, Santiago

China Fujian Zijin Mining and Metallurgical Testing, Xiamen

Côte d'Ivoire Bureau Veritas Mineral Laboratories, Abidjan

ENVAL, Yamoussoukro

Ghana ALS Minerals, Kumasi

Intertek Minerals, Samahu

Guyana MSALABS, East Coast Demerara.

Ireland ALS Minerals, Loughrea

Kyrgyz Republic Stewart Assay and Environmental Laboratories LLC, Kara-

Laos ALS Geochemistry, Vientiane

Mali Bureau Veritas, Mali

MSALABS, Bamako

MexicoBV Minerals, HermosilloMangoliaALS Minerals, Ulaanbaatar

ALS Mongolia, You Tolgoi

Morocco REMINEX Research Center, Casablanca

New Zealand SGS New Zealand Ltd, Otago

SGS New Zealand Ltd, Waihi

Peru ALS Minerals, Lima

Minera Yanacocha SRL - Newmont, Lima

Romania ALS Minerals, Rosia Montana

South Africa ALS Minerals, Edenvale – Johannesburg

Tanzania MSA Laboratories, Mwanza

Turkey ALS Minerals, Izmir USA ALS Minerals, Reno

Bureau Veritas Commodities and Trade, Sparks

Nevada Gold Mines, Goldstrike McClelland Laboratories, Sparks

Zimbabwe Performance Laboratories, Ruwa

Instructions and Recommendations for Use:

Weigh out quantity usually used for analysis and analyse for total gold by normal procedure. Homogeneity testing has shown that consistent results are obtainable for gold when 30g portions are taken for analysis.

We quote a 95% confidence interval for our estimate of the declared value. This confidence interval reflects our uncertainty in estimating the true value for the gold content of the reference material. The interval is chosen such that, if the same procedure used here to estimate the declared value were used again and again, 95% of the trials would give intervals that contained the true value. It reflects how precise the trial has been in estimating the declared value. It **does not** reflect the variability any particular laboratory will experience in its own repetitive testing.

Some users have used our consensus testing statistical data to establish control limits for assessing acceptance of laboratory results. Our certification process produces precise statistical data based on the proficiency program and not on an individual laboratory. Such use inevitably leads to many apparent out-of-control points, leading to doubts about the laboratory's testing, or of the reference material itself.

Our suggested best practice would be to accumulate a history of the test results obtained and plot them on a control chart to determine any laboratory bias and variability. The appropriate centre line and control limits for this chart should be based on the average level and variation exhibited in the laboratory's **own** data. This chart will provide a clear picture of the long-term stability or otherwise of the laboratory testing process, providing good clues as to the causes of any problems. To help our customers do this, we can provide a free Excel template that will produce sensible graphs, with intelligently chosen limits, from the customer's own data.

Our instructions are recommendations for the appropriate use of reference materials. If our statistical data is used for control limits due to practicality and particular circumstances, please consult with us and we will be happy to assist and advise.

Legal Notice:

This certificate and the reference material described in it have been prepared with due care and attention. However, Scott Technology Ltd and Nano Consulting Ltd accept no liability for any decisions or actions taken following the use of the reference material.

References:

For further information on the preparation and validation of this reference material please contact Eoin Foster.

Certifying Officer

Coin Foster

Independent Statistician

Daniel Walsh

Dr Daniel Walsh, PhD

Eoin Foster Manufacturing Manager